



Eurothane® GP

Eurothane GP is a thermal insulation board. Its core consists of rigid polyisocyanurate PIR foam. The board is faced with a gas diffusion tight multilayer foil on both sides. Grid pattern on both sides.

Application(s)

Thermal insulation of Pitched roofs, Framed walls, Floors (compatible with underfloor heating systems).

Board

Description	Value	Unit	Tolerances	Standard
Dimensions				
Length	2400	mm		
Width	1200	mm		
Thickness range	25 – 160	mm	T2	EN 823
Density (core volume weight)	± 30	kg/m ³		
Appearance				
Facing	Gas diffusion tight multilayer foil on both sides and grid on both sides.			
Edge finishing	Straight edges			

Essential characteristics

Description	Standard	EN code	Value	Unit
Thermal conductivity (declared value)				
All thicknesses	EN 13165	λ_D	0.022	W/m.K
Mechanical properties				
Compressive stress or compressive strength at 10% deformation thickness <50 mm	EN 826	CS(10/γ)120	≥120	kPa
Compressive stress or compressive strength at 10% deformation thickness 50-160 mm	EN 826	CS(10/γ)140	≥140	kPa
Fire behaviour				
Reaction to fire (product as such)	EN 13501-1	Euroclass	F	

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.com

FEEL
GOOD
INSIDE

RECTICEL
insulation

Fire performance

BS 476
(part 7)

Class 1

Hygrometric properties

Water vapour diffusion coefficient (foam)

EN ISO
10456

μ

50 - 100

(tab.
values)

Insulation Values

Thickness (mm)	λ D-value (W/mK)	RD-value (m ² K/W)
25	0.022	1.10
30	0.022	1.35
40	0.022	1.80
50	0.022	2.25
60	0.022	2.70
65	0.022	2.95
70	0.022	3.15
75	0.022	3.40
80	0.022	3.60
85	0.022	3.85
90	0.022	4.05
100	0.022	4.50
110	0.022	5.00
120	0.022	5.45
130	0.022	5.90
140	0.022	6.35
150	0.022	6.80
160	0.022	7.25

Standards & Certificates

Standards

Product standard	EN 13165:2012 + A2:2016
Production	ISO 9001:2015
Environmental management	ISO 14001:2015

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.com

FEEL
GOOD
INSIDE

RECTICEL
insulation

Certificates

BBA

Certificate 02/3905

(25-160mm)

Other / Miscellaneous

Production plant

Stoke-on-Trent

Enterprise Way, Whittle road, Meir park Stoke-on-Trent Staffordshire ST3 7UN

Storage/handling

The packaging in which the product is supplied, is not suitable for outside storage. Boards should be kept, dry, stored clear of the ground and covered with a weatherproof sheet, and protected from direct sunlight. Boards that have been allowed to get wet, should not be used.

Care has been taken to ensure that the content of this document is as accurate as possible. Please note that technical specifications may vary from country to country. Recticel Insulation does not accept any liability for clerical errors and reserves the right to amend information without prior notice. This document does not create, specify, modify or replace any new or prior contractual obligations agreed upon in writing between Recticel Insulation and the user.

Recticel Insulation

Zuidstraat 15, 8560 Wevelgem, Belgium

www.recticelinsulation.com

FEEL
GOOD
INSIDE

