

TECHNICAL DATA SHEET

TRAVIS PERKINS READY MIXED FILLER

A ready to use, ready mixed filler suitable for both interior and exterior uses. Ideal for repairs to all stonework, timber and plaster. Simple to use, dries white. May be sanded when dry, although this is often unnecessary, as the product is extremely smooth. When using externally, product must be sealed with oil based paint or varnish when dry.

USES

Travis Perkins Ready Mixed Filler is suitable for interior and exterior use. Ideal for repairs to plaster, plasterboard, brick, wood and stone.

COLOURS: Opaque white

PACKAGING: 600g packed 1 x 6
1kg packed 1 x 6

PREPARATION

Ensure surfaces are clean, dry and dust free. If necessary, stir filler before use.

APPLICATION

Apply in a thin layer using a filling knife or spatula, pressing into cavities. If a deeper repair is required, build up the filler in thinner layers. For a perfect finish, fill slightly proud of the surrounding surface and use fine sand paper to blend in the repair.

FINISHING

Protect from rain and water during setting. Exterior repairs should be overpainted with an oil based paint to protect from weathering. After use, ensure lid is firmly in place. Clean tools with water before filler sets hard.

HEALTH & SAFETY

Do not consume. Keep away from children and animals. If filler comes into contact with skin, wash with warm water before filler dries.

TRAVIS PERKINS READY MIXED FILLER TECHNICAL DATA SHEET

LIMITATIONS

Do not use on surfaces regularly under water. Do not use to glaze complete windows. An adhesion test prior to application is recommended. It is the users responsibility to determine suitability.

LIABILITY

The information given is the result of our tests and experience and is believed to be accurate and reliable. However as Siroflex Limited cannot know all the uses its products may be put to, it is the user's responsibility to determine suitability of use.

TECHNICAL DATA

Specification

Physical state	Paste
Form/ colour	Opaque
Odour	Mild
Specific gravity	1.910 +/- 0.05
Viscosity	2800 - 3500 Poise
pH	8.5 – 9.5
Solubility in water	Miscible